

US006440755B1

(12) United States Patent

Ramotowski

(10) Patent No.: US 6,440,755 B1 (45) Date of Patent: Aug. 27, 2002

(54)	METHOD FOR INCREASING FRACTURE
` ´	TOUGHNESS AND REDUCING
	BRITTLENESS OF FERROELECTRIC
	POLYMER

(75) Inventor: Thomas S. Ramotowski, Tiverton, RI

(US)

(73) Assignee: The United States of America as represented by the Secretary of the

Navy, Washington, DC (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35

U.S.C. 154(b) by 0 days.

(21) Appl. No.: 09/922,309

(22) Filed: Jul. 30, 2001

(51) Int. Cl.⁷ H01L 21/00

257/769; 438/3, 255, 758, 778, 781

(56) References Cited

U.S. PATENT DOCUMENTS

3,872,318 A * 3/1975 Murayama 307/88	3,872,318	Α	*	3/1975	Murayama		307/88
--------------------------------------	-----------	---	---	--------	----------	--	--------

4,348,611 A	٠	9/1982	Ruppel et al 313/388
			Vaarstra et al 438/758
6,180,420 B1	٠	1/2001	Hintermaier et al 438/3
6,323,511 B1	٠	11/2001	Marsh 257/295

* cited by examiner

ads (Mrads).

Primary Examiner—David Nelms Assistant Examiner—Dao H Nguyen

(74) Attorney, Agent, or Firm-Michael J. McGowan; Michael F. Oglo; Prithvi C. Lall

(57) ABSTRAC

A method is provided that increases fracture toughness and reduces brittleness of a semi-crystalline ferroelectric polymer material while substantially maintaining ferroelectric properties of the material. The material is heated in an inert oxygen-free atmosphere to a temperature above the material's Curie transition but below its melting temperature. The material is then irradiated with beta particles to provide a desired level of fracture toughness that substantially maintains ferroelectric properties of the material. In the case of poly(vinylidene fluoride-trifluorethylene), the heating temperature is just above the material's Curie transition temperature, the beta particles have an energy level of approximately 2.5 mega electron volts (MeV), and the radiation dose should not exceed approximately 50 megar-

20 Claims, 2 Drawing Sheets

